



G&E BLENDED EPDM 565

G&E Blended EPDM 565 is made from feedstock from various suppliers. The feedstocks are chosen to produce a blended EPDM polymer which has a high ethylene content, medium mooney and medium unsaturation. G&E Blended EPDM 565 can be blended with prime EPDM polymers to reduce compound costs in extruded, calendered and molded applications.

TYPICAL PROPERTIES

Mooney Viscosity (ML 1+4 @ 125°C)	50 ± 10
Raw Polymer Specific Gravity	0.88
Volatile matter, % weight	1.0 max.
Ethylene Content	High
3rd Monomer	Medium

PACKAGING

Material is packaged in low-melt polyethylene bags weighing 33 lbs. (15 kg.) each. There are 49 bags packaged in corrugated boxes on heat-treated pallets, each weighing approximately 1,620 lbs. (.735 MT).

The information contained herein is based upon laboratory tests believed to be reliable. However, it is offered solely for guidance to persons who will make their own determination. Goldsmith & Eggleton's products are sold without warranty, expressed or implied.